



# CF SANTA FE


## INSULATED METAL WALL PANEL

The Metl-Span CF Santa Fe panel has a flat exterior profile with a heavy, embossed stucco texture that mimics the look of a masonry stucco finish but with the added value of an insulated metal panel. The profile is flush with the warmth of an old-world finish, providing a visually pleasing building.


Note: Not intended for exterior walls on cold storage buildings.

LOCK & GROOVE SYSTEM

PANEL



PANEL PROFILE



### PRODUCT SPECIFICATIONS

- WIDTH** • 24", 30", 36", 42"
- THICKNESS** • 2", 2½", 2¾", 3", 4"
- LENGTH** • 8'-0" to 32'-0" Sante Fe horizontal embossed  
• 8'-0" to 40'-0" Sante Fe vertical embossed
- EXTERIOR PROFILE** • Flat profile with heavy embossing resembling old-world hand plaster
- EXTERIOR FACE** • G-90 galvanized or AZ-50 aluminum-zinc coated steel in 24 and 22 Ga.
- INTERIOR PROFILE** • Light Mesa, nominal ¼" deep, embossed or unembossed
- INTERIOR FACE** • G-90 galvanized or AZ-50 aluminum-zinc coated in 26, 24 and 22 Ga.

**JOINT** • Offset double tongue-and-groove with extended metal shelf for positive face fastening

**REVEAL** • Up to 3" reveal options in ¼", ½", ¾" and 1" increments

#### U-FACTORS AND R-VALUES\*\*

##### U-FACTOR (BTU/h-ft<sup>2</sup>·°F) PANEL WIDTH: 42"

	75°
2"	0.0669
2½"	0.0500
2¾"	0.0450
3"	0.0400
4"	0.0307

##### R-VALUE (h-ft<sup>2</sup>·°F/BTU) PANEL WIDTH: 42"

	75°
2"	14.95
2½"	20.00
2¾"	22.50
3"	25.00
4"	32.57

\*Available only from Nevada plant

\*\*Based on ASTM C518, ASTM C1363 and thermal modeling, 75° F core mean temp.

### DESIGN FEATURES & BENEFITS

- Masonry stucco appearance
- Utilizes concealed clips and eliminates thermal short circuits
- Easy and fast installation, with reduced construction labor costs
- Interior and exterior applications
- Can be used in conjunction with other Metl-Span joint profiles

# TESTING: CF SANTA FE INSULATED METAL WALL PANEL

TEST/APPROVAL	TEST METHOD	TEST TITLE	RESULTS
<b>Fire US</b>	ASTM E84	Surface Burning Characteristics of Building Materials	Flame spread <25, smoke developed <450
	ASTM E119	Fire Tests of Building Construction Materials	One hour non-load-bearing rating with two layers of Type X Gypsum Vertical or horizontal installation
	FM 4880	Class 1 Fire Rating of Insulated Wall, Ceiling and Roof Panels	Product approved Exterior wall requires FM 4881 approval
	NFPA 259	Test Method for Potential Heat of Building Materials	Potential heat of foam plastic insulation contained in the assembly tested in accordance with NFPA 285
	NFPA 285	Evaluation of Fire Propagation Characteristics of Exterior Non-Load-Bearing Wall Assemblies	Panel assembly met the requirements of the standard
	NFPA 286	Fire Tests for Evaluating Contribution of Wall and Ceiling Finish to Roof Fire Growth	Test specimen met the criteria of the IBC Section 803.1.2.1
<b>Fire Canada</b>	CAN/ULC S101	Fire Endurance Tests of Building Construction and Materials	One hour non-load-bearing fire rating with two layers of Type X Gypsum
	CAN/ULC S101	Fire Endurance Tests of Building Construction and Materials	Meets 15 minute stay-in-place requirements
	CAN/ULC S102	Surface Burning Characteristics of Building Materials and Assemblies	Meets the National Building Code of Canada requirements
	CAN/ULC S134	Fire Test of Exterior Wall Assemblies	Complies with the fire-spread and heat-flux limitations required by the National Building Code of Canada
	CAN/ULC S138	Fire Growth of Insulated Building Panels in a Full-Scale Room Configuration	Met the criteria of the standard
<b>Structural</b>	ASTM E72	Strength Tests of Panels for Building Construction	See Load Chart
	ASTM E1592	Structural Performance of Metal Roof and Siding Systems by Uniform Static Air Pressure Differences	See Load Chart
	FM 4881	Class 1 Exterior Wall Structural Performance	See FM Wall Load Chart
<b>Thermal Performance</b>	ASTM C518	Steady-State Thermal Transmission Properties by Means of the Heat-Flow Meter Apparatus	K-Factor of 0.126 BTU.in/hr.ft <sup>2</sup> .°F at 40° F mean core K-Factor of 0.14 BTU.in/hr.ft <sup>2</sup> .°F at 75° F mean core
	ASTM C1363	Thermal Performance of Building Materials and Envelope Assemblies	See Thermal Performance Guide
<b>Air Infiltration</b>	ASTM E283	Rate of Air Leakage Through Curtain Walls Under Specified Pressure Differences	<0.01 cfm/ft <sup>2</sup> at 20 psf Vertical or horizontal installation
<b>Water Infiltration</b>	ASTM E331	Water Penetration of Exterior Walls by Uniform Static Air Pressure Differences	No uncontrolled leakage when tested to a static pressure of 20 psf Vertical or horizontal installation
<b>Special Approval</b>	Miami-Dade NOA	Product Approval for City of Miami and Dade County	Product has City of Miami and Dade County Notice of Acceptance
	State of Florida	Product Approval for the State of Florida	Product has State of Florida approval

Descriptions and specifications contained herein were in effect at the time this publication was approved for printing. In a continuing effort to refine and improve products, Metl-Span reserves the right to discontinue products at any time or change specifications and/or designs without incurring obligation. To ensure you have the latest information available, please inquire or visit our website at [metlspan.com](http://metlspan.com).